

POLY VINYL ACETATE (HOMOPOLYMER) JP 52/G



DESCRIPTION

JP 52/G is a Poly Vinyl Acetate Homopolymer dispersion in water with copolymer, its principal properties include a long shelf life, Low viscosity and very good bonding properties, and it has an excellent water resistance.

SPECIFICATIONS:

Appearance	White viscous liquid
Type of Collide	Poly Vinyl Alcohol
Solid Content	50 \pm 2%
Viscosity at 25 C° Poise	12 \pm 3
Specific Gravity gr/ml	1.08
PH	2.0 – 3.0
MFFT C°	12

Note:

(MFFT): Minimum Film Formation Temperature

APPLICATIONS:

Primarily used in carpet backing.

SOLUBILITY:

Thinning is normally done with water though this will reduce the solid content. Solvents can be added to obtain a better freeze-thaw stability e.g. alcohols & glycols.

PACKAGING:

IBC Tanks & Plastic Drums 1000 Kg, 150 Kg Net.

STORAGE AND STABILITY:

This product must be stored in its (original, recondition) sealed plastic drum, in a dry place away from fire, heat source, spark and direct sunlight in temperatures between 5-30 C°.

Under these conditions, the shelf life will be 12 months from Production date.